



BULLETIN #1023-1

# TECHNICAL BULLETIN

## Foam Compatibility — ARCTIC 3% DB AFFF & ANSULITE AFC-3A AFFF


### **Introduction**

This study was undertaken to determine if SOLBERG® ARCTIC™ 3% DB AFFF Foam Concentrate is compatible when mixed with TYCO/ANSUL ANSULITE AFC-3A AFFF. Since neither Underwriters Laboratories, Inc. (UL) nor Factory Mutual (FM) possess any type of compatibility testing protocol, the compatibility test protocol for the U.S. Military specification for AFFF, Mil-F-24385F, was followed. In this specification, admixtures of the two concentrates are prepared at various ratios. These mixtures are tested for foam quality immediately after being prepared and again after being subjected to storage at 50 °C in tightly closed containers for a period of 10 days. In addition to the foam quality testing, the samples are visually inspected for any signs of incompatibility such as precipitation, haziness, gelling, layering, etc.

### **Sample Preparation**

Production lot number W1500249 of the ARCTIC foam concentrate and production lot number 2601 of the ANSULITE foam concentrate were used in the study. Mixtures of the Solberg and Tyco/Ansul foam concentrates were prepared as follows:

<b>SOLBERG % BY WEIGHT</b>	<b>TYCO/ANSUL % BY WEIGHT</b>
0	100
25	75
50	50
75	25
100	0



**SOLBERG is a member of PERIMETER SOLUTIONS, a global producer of leading fire retardant, gel and foam brands with a singular purpose: revolutionize the course of fire suppression technology with safer, more effective and more sustainable solutions. Together, we are Moving Industries Forward by Redefining Fire Suppression. [www.solbergfoam.com](http://www.solbergfoam.com)**



**Analytic Data** (TY = TYCO / SO = SOLBERG)

**Foam quality before temperature conditioning:**  
(EXP = Expansion value & 50% Drain = Drain time Min:Sec)

100% TY / 0% SO	75% TY / 25% SO	50% TY / 50% SO	25% TY / 75% SO	0% TY / 100% SO
EXP = 5.3 50% Drain = 7:14	EXP = 5.4 50% Drain = 6:56	EXP = 5.5 50% Drain = 6:58	EXP = 5.7 50% Drain = 6:31	EXP = 5.7 50% Drain = 7:45

**Foam quality after temperature conditioning:**  
(EXP = Expansion value & 50% Drain = Drain time Min:Sec)

100% TY / 0% SO	75% TY / 25% SO	50% TY / 50% SO	25% TY / 75% SO	0% TY / 100% SO
EXP = 5.8 50% Drain = 7:22	EXP = 6.0 50% Drain = 7:06	EXP = 5.6 50% Drain = 7:01	EXP = 5.9 50% Drain = 6:44	EXP = 5.7 50% Drain = 7:12

**Discussion of Results**

Both before and after temperature conditioning, all of the samples were clear liquids, water white to light straw colored with no signs of precipitation, gelling, layering or any other notable condition. The foam quality values showed no signs of deterioration after the temperature conditioning. In fact, many values actually increased slightly over the values obtained before the temperature conditioning.

**Conclusion**

SOLBERG ARCTIC 3% DB AFFF foam concentrate and TYCO/ANSUL ANSULITE AFC-3A AFFF foam concentrate are completely compatible when mixed at all ratios.



NOTICE: Perimeter Solutions makes no representations or warranties as to the completeness or accuracy of the information included herein. The information contained herein is not intended to provide regulatory, legal or expert advice relating to the products, its application or uses. Nothing contained herein is to be construed as a recommendation to use any product, process, equipment or formulation in conflict with any industrial property or intellectual property rights, and Perimeter Solutions makes no representation or warranty, express or implied, that the use thereof will not infringe on any industrial property or intellectual property rights. NO REPRESENTATIONS OR WARRANTIES, EITHER EXPRESSED OR IMPLIED, OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE OR OF ANY OTHER NATURE ARE MADE HEREUNDER WITH RESPECT TO THE INFORMATION CONTAINED HEREIN.

SOLBERGFOAM.COM

TECHNICAL BULLETIN TB-1023-11 | JUNE 2016

COPYRIGHT © 2016  
SOLBERG AND ARCTIC ARE TRADEMARKS OF PERIMETER SOLUTIONS  
OR ITS AFFILIATES. ANSUL AND ANSULITE ARE TRADEMARKS OF TYCO.

**AMERICAS**  
PERIMETER SOLUTIONS, LP  
1520 Brookfield Avenue  
Green Bay, WI 54313  
USA  
Tel: +1 920 593 9445

**EMEA**  
PERIMETER SOLUTIONS, LP  
Polígono de Baiña, Parcela 23  
33682 Mieres (Asturias)  
Spain  
Tel: +34 985 24 29 45

**ASIA PACIFIC**  
PERIMETER SOLUTIONS, LP  
3 Charles Street  
St. Marys NSW 2760  
Australia  
Tel: +61 2 9673 5300